



Catalog N°: 59630

Agency Approvals / Specifications	CFIA Listed
Color	Red
Cure Type	Room Temperature Vulcanization (RTV) Cure
Fixture Time	30 min.
Full Cure Temperature (°C)	25
Full Cure Temperature (°F)	77
Full Cure Time	24 hr.
Physical Form	Paste
Technology	Silicone
Temperature Range (°C)	-59 to 316
Temperature Range (°F)	-75 to 600

